



US007821024B2

(12) **United States Patent**
Jeong

(10) **Patent No.:** **US 7,821,024 B2**
(45) **Date of Patent:** **Oct. 26, 2010**

(54) **SEMICONDUCTOR LIGHT EMITTING DEVICE HAVING ROUGHNESS LAYER**

(75) Inventor: **Hwan Hee Jeong**, Ulsan (KR)

(73) Assignee: **LG Innotek Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 66 days.

(21) Appl. No.: **12/340,354**

(22) Filed: **Dec. 19, 2008**

(65) **Prior Publication Data**

US 2009/0159917 A1 Jun. 25, 2009

(30) **Foreign Application Priority Data**

Dec. 20, 2007 (KR) 10-2007-0133919

(51) **Int. Cl.**

H01L 33/00 (2010.01)

(52) **U.S. Cl.** **257/98; 257/E33.063**

(58) **Field of Classification Search** **257/98, 257/E33.006, E33.062, E33.063**

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,441,403 B1 * 8/2002 Chang et al. 257/94
6,469,324 B1 * 10/2002 Wang 257/98

* cited by examiner

Primary Examiner—Thomas L Dickey

(74) *Attorney, Agent, or Firm*—Birch, Stewart, Kolasch & Birch, LLP

(57) **ABSTRACT**

A semiconductor light emitting device includes a first conductive semiconductor layer, an active layer on the first conductive semiconductor layer, and a second conductive semiconductor layer on the active layer, and a roughness layer on the second conductive semiconductor layer. The second conductive semiconductor layer includes a shape of multiple horns, and the roughness layer includes a shape of multiple horns. The second conductive semiconductor layer includes a roughness in which horn shapes and inverse-horn-shaped shapes are alternately formed, and the roughness has a height of about 0.5 μm to about 1.2 μm and a diameter of about 0.3 μm to about 1.0 μm .

29 Claims, 9 Drawing Sheets




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8





FIG. 9



SEMICONDUCTOR LIGHT EMITTING DEVICE HAVING ROUGHNESS LAYER

CROSS-REFERENCE TO RELATED APPLICATIONS

The present application claims priority under 35 U.S.C. 126 to Korean Patent Application No. 10-2007-0133919 (filed on Dec. 20, 2007), which is hereby incorporated by reference in its entirety.

BACKGROUND

The present disclosure relates to a semiconductor light emitting device.

Group III-V nitride semiconductors have been variously applied to an optical device such as blue and green light emitting diodes (LED), a high speed switching device, such as a MOSFET (Metal Semiconductor Field Effect Transistor) and an HEMT (Hetero junction Field Effect Transistors), and a light source of a lighting device or a display device.

The nitride semiconductor is mainly used for the LED (Light Emitting Diode) or an LD (laser diode), and studies have been continuously conducted to improve the fabrication process or light efficiency of the nitride semiconductor.

SUMMARY

Embodiments provide a semiconductor light emitting device comprising a second conductive semiconductor layer with a dual roughness structure.

Embodiments provide a semiconductor light emitting device comprising a second conductive semiconductor layer with a horn-shaped dual roughness structure.

Embodiments provide a semiconductor light emitting device, which is capable of enhancing external quantum efficiency by forming a horn-shaped dual roughness structure in a second conductive semiconductor layer.

An embodiment provides a semiconductor light emitting device comprising: a first conductive semiconductor layer; an active layer on the first conductive semiconductor layer; and a second conductive semiconductor layer comprising a dual roughness structure on the active layer.

An embodiment provides a semiconductor light emitting device comprising: a first conductive semiconductor layer; an active layer on the first conductive semiconductor layer; and a second conductive semiconductor layer on the active layer, wherein the second conductive semiconductor layer comprises: a first semiconductor layer comprising a shape of multiple horns; and a roughness layer ohmic-contacted on the first semiconductor layer.

An embodiment provides a semiconductor light emitting device comprising: a substrate; a first conductive semiconductor layer on the substrate; an active layer on the first conductive semiconductor layer; and a second conductive semiconductor layer comprising a dual roughness structure of a shape a multiple horns on the active layer.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a side sectional view of a semiconductor light emitting device according to a first embodiment.

FIGS. 2 through 7 are sectional views illustrating a method for fabricating a semiconductor light emitting device according to a first embodiment.

FIG. 8 is a side sectional view of a semiconductor light emitting device according to a second embodiment.

FIG. 9 is a side sectional view of a semiconductor light emitting device according to a third embodiment.

DETAILED DESCRIPTION OF THE EMBODIMENTS

Hereinafter, a semiconductor light emitting device according to the embodiment will be described with reference to the accompanying drawings. In the description of the embodiment, it will be understood that, when a layer (or film), a region, a pattern, or a structure is referred to as being "on (above/over/upper)" or "under(below/down/lower)" another substrate, another layer (or film), another region, another pad, or another pattern, it can be directly on the other substrate, layer (or film), region, pad or pattern, or intervening layers may also be present. Furthermore, it will be understood that, when a layer (or film), a region, a pattern, a pad, or a structure is referred to as being "between" two layers (or films), regions, pads, or patterns, it can be the only layer between the two layers (or films), regions, pads, or patterns or one or more intervening layers may also be present. Thus, it should be determined by technical idea of the invention.

FIG. 1 is a side sectional view of a semiconductor light emitting device according to a first embodiment. Referring to FIG. 1, a semiconductor light emitting device 100 comprises a substrate 110, a buffer layer 120, a first conductive semiconductor layer 130, an active layer 140, a second conductive semiconductor layer 150 having dual roughness 152 and 156, a first electrode 171, and a second electrode 173.

The substrate 110 may be formed of a material selected from the group consisting of sapphire (Al_2O_3), GaN, SiC, ZnO, Si, GaP, and GaAs. Concave-convex patterns may be formed on the substrate 110, but the present invention is not limited thereto.

The buffer layer 120 is formed on the substrate 110. The buffer layer 120 is a layer for reducing a lattice constant difference from the substrate 110. The buffer layer 120 may be formed to a predetermined thickness (for example, about 140 Å to about 1,000 Å) by selectively using GaN, AlN, AlGaIn, InGaIn, or AlInGaIn.

An undoped semiconductor layer (not shown) may be formed on the buffer layer 120 or the substrate 110. The undoped semiconductor layer (not shown) may comprise an undoped GaN-based layer. Neither of the buffer layer 120 and the undoped semiconductor layer (not shown) may be formed on the substrate 110, or at least one of them may be formed on the substrate 110.

At least one first conductive semiconductor layer 130 is formed on the buffer layer 120. The first conductive semiconductor layer 130 is a semiconductor layer doped with a first conductive dopant. The first conductive semiconductor layer 130 may be formed of a semiconductor material having a composition formula of $\text{In}_x\text{Al}_y\text{Ga}_{1-x-y}\text{N}$ ($0 \leq x \leq 1$, $0 \leq y \leq 1$, $0 \leq x+y \leq 1$), for example, InAlGaIn, GaN, AlGaIn, InGaIn, AlN, or InN. When the first conductive semiconductor layer 130 is an N-type semiconductor layer, the first conductive dopant is an N-type dopant, such as Si, Ge, or Sn.

The active layer 140 is formed on the first conductive semiconductor layer 130. The active layer 140 may have a single quantum well structure or a multiple quantum well structure. The active layer 140 may be formed of InGaIn/GaN or AlGaIn/GaN by using group III-V compound semiconductors.

The active layer 140 is formed of a material having a bandgap energy according to a light wavelength at which light is emitted. For example, in the case of a blue light emission having a wavelength range from 460 nm to 470 nm, the active

layer **140** may be formed in a single or multiple quantum well structure at a period of an InGaN well layer/GaN barrier layer. The active layer **140** may comprise a material emitting a colored light such as a blue wavelength light, a red wavelength light, and a green wavelength light. A conductive clad layer (not shown) may be formed over and/or under the active layer **140**, and the conductive clad layer (not shown) comprises an AlGaIn-based layer.

The second conductive semiconductor layer **150** is formed on the active layer **140**. The second conductive semiconductor layer **150** is a semiconductor layer doped with a second conductive dopant. The second conductive semiconductor layer **150** may be formed of a semiconductor material having a composition formula of $\text{In}_x\text{Al}_y\text{Ga}_{1-x-y}\text{N}$ ($0 \leq x \leq 1$, $0 \leq y \leq 1$, $0 \leq x+y \leq 1$), for example, InAlGaIn, GaN, AlGaIn, InGaIn, AlN, or InN. When the second conductive semiconductor layer **150** is a P-type semiconductor layer, the second conductive dopant is a P-type dopant, such as Mg, Zn, Ca, Sr, or Ba.

The first conductive semiconductor layer **130**, the active layer **140**, and the second conductive semiconductor layer **150** serve as a light emitting structure. The light emitting structure may be formed in one of an N—P junction structure, a P—N junction structure, an N—P—N junction structure, and a P—N—P junction structure.

The second conductive semiconductor layer **150** comprises a first semiconductor layer **151** and a roughness layer **155**.

The first semiconductor layer **151** is a P-type semiconductor layer doped with a second conductive dopant and may be formed of InAlGaIn, GaN, AlGaIn, InGaIn, AlN, or InN. The first semiconductor layer **151** has a first roughness **152** on the top surface thereof, and the first roughness **152** may be formed in a shape of multiple horns.

The first roughness **152** may have a structure in which horn-shaped apex patterns and inverse-horn-shaped valley patterns are alternately arranged.

The first roughness **152** may have a height (H) of about 0.5 μm to about 1.2 μm and a diameter (D) of about 0.3 μm to about 1.0 μm . The height (H) of the first roughness **152** may be that of the horn-shaped apex pattern, and the diameter (D) of the first roughness **152** may be length between two apexes or between two valleys. The first roughness **152** may have a horn shape, a polygonal horn shape, or a random horn shape, and may be formed at irregular intervals.

The roughness layer **155** is formed on the first semiconductor layer **151**. The roughness layer **155** is a P-type semiconductor layer doped with a second conductive dopant and may be formed of InAlGaIn, GaN, AlGaIn, InGaIn, AlN, or InN.

The roughness layer **155** is ohmic-contacted with the first semiconductor layer **151** and may be formed to a predetermined thickness of about 1,000 \AA to about 2,000 \AA .

The roughness layer **155** is formed with a second roughness **156**. The second roughness **156** may be formed in the same shape as the first roughness **152**. The second roughness **156** may have a structure in which horn-shaped apex patterns and inverse-horn-shaped valley patterns are arranged regularly or irregularly.

The first semiconductor layer **151** and the roughness layer **155** may be formed of the same semiconductor materials or the different semiconductor materials.

The second electrode **173** is formed on the roughness layer **155** of the second conductive semiconductor layer **150**, and the second electrode **173** may have predetermined patterns. The first electrode **171** may be formed on or electrically connected to the first conductive semiconductor layer **130**.

By forming the first roughness and the second roughness having a shape of multiple horns in the second conductive semiconductor layer **150**, external quantum efficiency can be enhanced. That is, the horn-shaped first rough **152** and the horn-shaped second roughness **156** change the incident angle of light emitted from the active layer **140**, thereby enhancing light emission efficiency.

FIGS. **2** through **7** are sectional views illustrating a method for manufacturing a semiconductor light emitting device according to a first embodiment.

Referring to FIG. **2**, a buffer layer **120**, a first conductive semiconductor layer **130**, an active layer **140**, and a first semiconductor layer **151A** of a second conductive semiconductor layer are formed on a substrate **110**.

The substrate **110** may be formed of a material selected from the group consisting of sapphire (Al_2O_3), GaN, SiC, ZnO, Si, GaP, and GaAs. The buffer layer **120** is formed on the substrate **110** and may be formed of GaN, AlN, AlGaIn, InGaIn, or AlInGaIn. An undoped semiconductor layer (not shown) may be formed on the buffer layer **120** or the substrate **110**. The undoped semiconductor layer (not shown) may comprise an undoped GaIn-based layer. Neither of the buffer layer **120** and the undoped semiconductor layer (not shown) may be formed on the substrate **110**, or at least one of them may be formed.

At least one first conductive semiconductor layer **130** is formed on the buffer layer **120**. The first conductive semiconductor layer **130** may comprise an N-type semiconductor layer. The first conductive semiconductor layer **130** may be formed of a semiconductor material having a composition formula of $\text{In}_x\text{Al}_y\text{Ga}_{1-x-y}\text{N}$ ($0 \leq x \leq 1$, $0 \leq y \leq 1$, $0 \leq x+y \leq 1$), for example, InAlGaIn, GaN, AlGaIn, InGaIn, AlN, or InN. The first conductive semiconductor layer **130** comprises an N-type dopant, such as Si, Ge, or Sn.

The active layer **140** is formed on the first conductive semiconductor layer **130**. The active layer **140** may have a single quantum well structure or a multiple quantum well structure. The active layer **140** may be formed of InGaIn/GaN or AlGaIn/GaN by using group III-V compound semiconductors. The active layer **140** may comprise a material emitting a colored light such as a blue wavelength light, a red wavelength light, and a green wavelength light.

A conductive clad layer (not shown) may be formed over and/or under the active layer **140**. The conductive clad layer (not shown) comprises an AlGaIn-based layer.

The first semiconductor layer **151A** of the second conductive semiconductor layer is formed on the active layer **140**. The first semiconductor layer **151A** may comprise a P-type semiconductor layer. The first semiconductor layer **151A** may be formed of a semiconductor material having a composition formula of $\text{In}_x\text{Al}_y\text{Ga}_{1-x-y}\text{N}$ ($0 \leq x \leq 1$, $0 \leq y \leq 1$, $0 \leq x+y \leq 1$), such as InAlGaIn, GaN, AlGaIn, InGaIn, AlN, or InN. The first semiconductor layer **151A** may comprise a P-type dopant such as Mg, Zn, Ca, Sr, or Ba. The first semiconductor layer **151A** may be formed to a predetermined thickness of about 0.7 μm to about 1.5 μm .

Referring to FIGS. **3** and **4**, a removal layer **160** is formed on the first semiconductor layer **151A**. The removal layer **160** is formed in a thin film type by selectively using indium tin oxide (ITO), indium zinc oxide (IZO), aluminum zinc oxide (AZO), silver (Ag), and aluminum (Al).

A first etching process is performed on the removal layer **160**. The first etching process uses a wet etchant (for example, HCl solution) The removal layer **160** is formed in a shape of multiple island patterns **162** by a wet etching process.

The island patterns **162** may have an embossing shape, a semispherical shape, or a convex lens shape, or may be

formed regularly or irregularly with an irregular size and a random shape. The shape and size of the island patterns **162** may be different according to a material of the removal layer **160** or an etching degree.

Referring to FIGS. **4** and **5**, a second etching process is performed on the island patterns **162**. The second etching process may be performed by a dry etching process.

The second etching process may be performed from the multiple island patterns **162** to a predetermined portion of the first semiconductor layer **151A**.

The dry etching process may be performed by selectively using an Inductively Coupled Plasma (ICP) apparatus, a Reactive Ion Etching (RIE) apparatus, a Capacitively Coupled Plasma (CCP) apparatus, and an Electron Cyclotron Resonance (ECR) apparatus.

An etching depth of the first semiconductor layer **151A** is changed according to a material difference (strength difference) and a thickness difference of the island patterns **162**. Accordingly, the first semiconductor layer **151** has a first roughness **152** having a shape of multiple horns on the top surface thereof.

The first roughness **152** of the first semiconductor layer **151** is formed in an apex/valley patterns. The valley patterns are formed by a relatively thin island pattern region, and the apex patterns are formed by a relatively thick island pattern region.

The first roughness **152** of the first semiconductor layer **151** may be formed in a horn shape, a polygonal horn shape, or a random horn shape, and may be formed at dense intervals.

The first roughness **152** may have a height (H) of about 0.5 μm to about 1.2 μm and a diameter (D) of about 0.3 μm to about 1.0 μm .

Referring to FIG. **6**, a roughness layer **155** is formed on the first semiconductor layer **151**. The first semiconductor layer **151** and the roughness layer **155** define a second conductive semiconductor layer **150**.

The roughness layer **155** may be a P-type semiconductor layer. The roughness layer **155** may be formed of a semiconductor material having a composition formula of $\text{In}_x\text{Al}_y\text{Ga}_{1-x-y}\text{N}$ ($0 \leq x \leq 1$, $0 \leq y \leq 1$, $0 \leq x+y \leq 1$), for example, InAl-GaN , AlGaIn , InGaIn , AlIn , or InN . The roughness layer **155** may comprise a P-type dopant such as Mg, Zn, Ca, Sr, or Ba.

The roughness layer **155** may be formed to a predetermined thickness of about 1,000 \AA to about 2,000 \AA and is ohmic-contacted with the first semiconductor layer **151**. A second roughness **156** having the same shape as the first roughness **152** is formed in the roughness layer **155**.

The second conductive semiconductor layer **150** may have a structure in which a dual structure of the first roughness **152** and the second roughness **156** is formed in a horn shape.

Referring to FIG. **7**, a mesh etching process is performed to expose a portion of the first conductive semiconductor layer **130**.

A first electrode **171** is formed on the first conductive semiconductor layer **130**, and a second electrode **173** is formed on the second conductive semiconductor layer **150**.

In the semiconductor light emitting device **100** according to the current embodiment, the dual structure of the horn-shaped roughness **152** and **156** is formed in the second conductive semiconductor layer **150**. Thus, the incident angle of light emitted from the active layer **140** can be changed, thereby enhancing external quantum efficiency.

FIG. **8** is a side sectional view of a semiconductor light emitting device according to a second embodiment. In the

first and second embodiments, like reference numerals refer to like elements and duplicate description will be omitted.

Referring to FIG. **8**, the semiconductor light emitting device **100A** comprises a substrate **110**, a buffer layer **120**, a first conductive semiconductor layer **130**, an active layer **140**, a second conductive semiconductor layer **150** having dual roughness **152** and **156**, a transparent electrode layer **170**, a first electrode **171**, and a second electrode **173**.

The transparent electrode layer **170** is formed on the second conductive semiconductor layer **150** and may have a roughness structure.

The transparent electrode layer **170** may have a roughness with a shape of multiple horns along the roughness layer **155** of the second conductive semiconductor layer **150**. Accordingly, a triple structure of horn shaped roughness may be formed on the active layer **140**.

The transparent electrode layer **170** may comprise at least one of indium tin oxide (ITO), indium zinc oxide (IZO), indium zinc tin oxide (IZTO), indium aluminum zinc oxide (IAZO), indium gallium zinc oxide (IGZO), indium gallium tin oxide (IGTO), aluminum zinc oxide (AZO), antimony tin oxide (ATO), ZnO, RuOx, TiOx, IrOx, and SnO₂.

The second electrode **173** may be formed on the roughness layer **155** of the second conductive semiconductor layer **150**, or may be formed on the transparent electrode layer **170** and/or the roughness layer **155**.

FIG. **9** is a side sectional view of a semiconductor light emitting device according to a third embodiment. In the first and third embodiments, like reference numerals refer to like elements and duplicate description will be omitted.

Referring to FIG. **9**, the semiconductor light emitting device **100B** comprises a substrate **110**, a buffer layer **120**, a first conductive semiconductor layer **130**, an active layer **140**, a second conductive semiconductor layer **150** having dual roughness **152** and **156**, a third conductive semiconductor layer **170**, a first electrode **171**, and a second electrode **173**.

The third conductive semiconductor layer **175** may comprise an N-type semiconductor layer or a P-type semiconductor layer. For example, when the first conductive semiconductor layer **130** is an N-type semiconductor layer, the third conductive semiconductor layer **175** may be an N-type semiconductor layer. When the first conductive semiconductor layer **130** is a P-type semiconductor layer, the third conductive semiconductor layer **175** may be a P-type semiconductor layer.

The third conductive semiconductor layer **175** may have a roughness with a shape of multiple horns along the roughness layer **155** of the second conductive semiconductor layer **150**. Accordingly, a triple structure of horn-shaped roughness may be formed on the active layer **140**.

Furthermore, a transparent electrode layer (not shown) may be formed on the third conductive semiconductor layer **175**, and the transparent electrode layer (not shown) can diffuse a current to a whole region.

The second electrode **173** may be formed on the third conductive semiconductor layer **175**, but the present invention is not limited thereto.

The semiconductor light emitting device according to the current embodiment may be formed in a P—N structure, an N—P structure, an N—P—N structure, and a P—N—P structure. Accordingly, the second conductive semiconductor layer **150** may be implemented with an N-type semiconductor layer or a P-type semiconductor layer.

Any reference in this specification to “one embodiment,” “an embodiment,” “example embodiment,” etc., means that a particular feature, structure, or characteristic described in connection with the embodiment is comprised in at least one

embodiment of the invention. The appearances of such phrases in various places in the specification are not necessarily all referring to the same embodiment. Further, when a particular feature, structure, or characteristic is described in connection with any embodiment, it is submitted that it is within the purview of one skilled in the art to effect such feature, structure, or characteristic in connection with other ones of the embodiments.

Although embodiments have been described with reference to a number of illustrative embodiments thereof, it should be understood that numerous other modifications and embodiments can be devised by those skilled in the art that will fall within the spirit and scope of the principles of this disclosure. More particularly, various variations and modifications are possible in the component parts and/or arrangements of the subject combination arrangement within the scope of the disclosure, the drawings and the appended claims. In addition to variations and modifications in the component parts and/or arrangements, alternative uses will also be apparent to those skilled in the art.

What is claimed is:

1. A semiconductor light emitting device comprising:
 - a first conductive semiconductor layer;
 - an active layer on the first conductive semiconductor layer;
 - a second conductive semiconductor layer on the active layer; and
 - a roughness layer on the second conductive semiconductor layer,
 wherein the second conductive semiconductor layer includes a shape of multiple horns,
 wherein the roughness layer includes a shape of multiple horns, and
 wherein the second conductive semiconductor layer comprises a roughness in which horn shapes and inverse-horn-shaped shapes are alternately formed, and the roughness has a height of about 0.5 μm to about 1.2 μm and a diameter of about 0.3 μm to about 1.0 μm .
2. The semiconductor light emitting device according to claim 1, wherein the roughness layer has a thickness of about 1,000 \AA to about 2,000 \AA .
3. The semiconductor light emitting device according to claim 1, wherein the roughness has at least one of a horn shape, a polygonal horn shape, and a random horn shape.
4. The semiconductor light emitting device according to claim 1, further comprising an N-type or P-type semiconductor layer on the second conductive semiconductor layer, wherein the N-type or P-type semiconductor layer includes a horn-shaped roughness layer.
5. The semiconductor light emitting device according to claim 1, further comprising a transparent electrode layer on the second conductive semiconductor layer, wherein the transparent electrode layer includes a horn-shaped roughness layer.
6. The semiconductor light emitting device according to claim 1, further comprising at least one of an undoped semiconductor layer, a buffer layer, and a substrate under the first conductive semiconductor layer.
7. The semiconductor light emitting device according to claim 1, wherein the roughness layer includes the same conductivity type dopants as the second conductive semiconductor layer.
8. The semiconductor light emitting device according to claim 1, wherein the roughness layer includes a semiconductor layer.
9. The semiconductor light emitting device according to claim 1, wherein the diameter of the roughness is a length between two apexes or two valleys of the roughness.

10. A semiconductor light emitting device comprising:
 - a first conductive semiconductor layer;
 - an active layer on the first conductive semiconductor layer; and
 - a second conductive semiconductor layer on the active layer,
 wherein the second conductive semiconductor layer comprises a first semiconductor layer comprising a shape of multiple horns, and
 wherein the second conductive semiconductor layer comprises a roughness and the roughness has a height of about 0.5 μm to about 1.2 μm and a diameter of about 0.3 μm to about 1.0 μm .
11. The semiconductor light emitting device according to claim 10, wherein the first semiconductor layer has a structure in which horn-shaped apex structures and inverse-horn-shaped valley structures are formed regularly or irregularly.
12. The semiconductor light emitting device according to claim 10, wherein the diameter of the roughness is a length between two apexes or two valleys of the roughness.
13. The semiconductor light emitting device according to claim 10, further comprising a first roughness layer having an uneven upper surface and an uneven lower surface on the first semiconductor layer,
 wherein the first roughness layer has the roughness structure corresponding to the multiple horns shape of the first semiconductor layer.
14. The semiconductor light emitting device according to claim 13, wherein the first roughness layer includes the same conductivity type dopants as the first semiconductor layer.
15. The semiconductor light emitting device according to claim 13, wherein the first roughness layer includes a semiconductor layer.
16. The semiconductor light emitting device according to claim 13, further comprising a second roughness layer having an uneven upper surface and an uneven lower surface on the first roughness layer, wherein the second roughness layer is formed of at least one of a transparent electrode layer and a third conductive semiconductor layer having a horn-shaped roughness.
17. The semiconductor light emitting device according to claim 16, wherein one of the first roughness layer and the second roughness layer is partially disposed on the second conductive semiconductor layer, and wherein at least a portion of the first roughness layer is disposed between the second conductive semiconductor layer and the second roughness layer.
18. The semiconductor light emitting device according to claim 13, wherein the first semiconductor layer includes a P-type semiconductor layer,
 wherein the first roughness layer is formed of a different material from the first semiconductor layer.
19. A semiconductor light emitting device comprising:
 - a substrate;
 - a first conductive semiconductor layer on the substrate;
 - an active layer on the first conductive semiconductor layer;
 - a second conductive semiconductor layer on the active layer;
 - a first roughness layer on the second conductive semiconductor layer; and
 - a second roughness layer on the first roughness layer,
 wherein one of the first roughness layer and the second roughness layer is partially disposed on the second conductive semiconductor layer,
 wherein at least a portion of the first roughness layer is disposed between the second conductive semiconductor layer and the second roughness layer, and

wherein the second conductive semiconductor layer comprises a roughness and the roughness has a height of about 0.5 μm to about 1.2 μm and a diameter of about 0.3 μm to about 1.0 μm .

20. The semiconductor light emitting device according to claim 19, wherein the first roughness layer has a thickness of about 1,000 Å to about 2,000 Å.

21. The semiconductor light emitting device according to claim 19, further comprising a first electrode on the first conductive semiconductor layer; and a second electrode on the second conductive semiconductor layer,

wherein the second electrode is in direct contact with the second roughness layer.

22. The semiconductor light emitting device according to claim 19, further comprising an N-type or P-type semiconductor layer comprising a horn-shaped roughness structure on the second conductive semiconductor layer.

23. The semiconductor light emitting device according to claim 19, further comprising a transparent electrode layer comprising a horn-shaped roughness structure on the second conductive semiconductor layer.

24. The semiconductor light emitting device according to claim 19, wherein the first roughness layer has an uneven upper surface and an uneven lower surface, and wherein the second roughness layer has an uneven upper surface and an uneven lower surface.

25. The semiconductor light emitting device according to claim 19, wherein the second conductive semiconductor layer comprises a roughness having a height of about 0.5 μm to about 1.2 μm and a diameter of about 0.3 μm to about 1.0 μm .

26. The semiconductor light emitting device according to claim 19, wherein the second roughness layer includes one of ITO(indium tin oxide), IZO(indium zinc oxide), IZTO(indium zinc tin oxide), IAZO(indium aluminum zinc oxide), IGZO(indium gallium zinc oxide), IGTO(indium gallium tin oxide), AZO(aluminium zinc oxide), ATO(antimony tin oxide), ZnO, RuO_x, TiO_x, IrO_x, or SnO₂.

27. The semiconductor light emitting device according to claim 19, wherein the first roughness layer is entirely disposed on the second conductive semiconductor layer, and wherein the second roughness layer is partially disposed on the second conductive semiconductor layer.

28. The semiconductor light emitting device according to claim 19, wherein the second conductive semiconductor layer includes a P-type semiconductor layer,

wherein the first roughness layer is formed of a different material from the second conductive semiconductor layer.

29. The semiconductor light emitting device according to claim 19, wherein the diameter of the roughness is a length between two apexes or two valleys of the roughness.

* * * * *